



# LUMISEAL PLUS™

DS-172.6-1214

A product brand of LATICRETE International, Inc.



## 1. PRODUCT NAME

LUMISEAL PLUS™

## 2. MANUFACTURER

LATICRETE International, Inc.  
1 LATICRETE Park North  
Bethany, CT 06524-3423 USA

Toll Free: 1.800.243.4788, ext. 235  
Telephone: +1.203.393.0010, ext. 235  
Fax: +1.203.393.1948  
Website: [www.lmcc.com](http://www.lmcc.com)

## 3. PRODUCT DESCRIPTION

LUMISEAL PLUS is a solvent based, non-yellowing, blush resistant curing and sealing compound. When used as a sealer, LUMISEAL PLUS is designed to provide an attractive high gloss finish on concrete substrates. LUMISEAL PLUS forms a very durable film with excellent early water-resistance to whitening or blistering. LUMISEAL PLUS is suitable for use on interior, exterior, horizontal and vertical surfaces.

The durable film of LUMISEAL PLUS bonds easily to clean concrete surfaces. It forms a non-yellowing protective film that assures improved resistance to contaminants, stains, and abrasion. LUMISEAL PLUS offers superior protection when used over properly densified surfaces.

The advanced self-crosslinking chemistry of LUMISEAL PLUS transforms the easy to spray, pure acrylic polymer solution into a very hard, clear resin film that resists abrasion, stain and tire marking.

## Uses

LUMISEAL PLUS is recommended to seal new and old concrete surfaces including decorative, colored, patterned patios, driveways, and walkways. Other applications include exposed aggregate, brick pavers, polished concrete and other concrete surfaces where a durable gloss and stain resistant sealer is required.

## Specification Description

03 39 13: Acrylic Curing Compound: Minimum 25% acrylic solids shall conform to ASTM C309, Type I, and ASTM C1315, Type 1.

## Advantages

- Non-blushing formula; resists whitening
- Non-yellowing, pure acrylic formulation
- Resists black tire marks
- Highlights the natural beauty of the surface
- Use on any clean concrete surface
- High gloss

## Suitable Substrates

- Freshly Placed Concrete
- Existing Concrete

## Packaging

1 Gal (3.8 L)  
5 Gal (19 L)  
55 Gal (208 L)

## Approximate Coverage

Surface porosity determines coverage rate. For best results:  
First coat, curing - 200-400 ft<sup>2</sup> /gal (4.8 to 9.8 m<sup>2</sup>/L)  
Decorative concrete - 300 ft<sup>2</sup> /gal (7.3 m<sup>2</sup>/L)  
Second coat, gloss - 400-600 ft<sup>2</sup>/gal (9.8 to 14.7 m<sup>2</sup>/L)

## Shelf Life

Containers are to be kept tightly sealed. Do not freeze. Store above 40°F (4°C). Stir well before using as some settlement will occur during storage. Shelf life is two years in factory-sealed containers when properly stored.

## Limitations

- Heavy applications should be avoided for proper film formation.
- For proper film development, apply only when the surface temperature is over 40°F (4°C) and the relative humidity is below 80%.

## Cautions

- Review Safety Data Sheet (SDS) for product safety information
- COMBUSTIBLE – KEEP AWAY FROM HEAT SOURCES
- Contains aromatic solvents
- Use with adequate ventilation
- Avoid contact with skin, eyes and clothing
- Wear skin and eye protection
- Wash thoroughly after handling
- Do not take internally
- Enhanced air circulation is desired to improve the drying rate and to remove organic solvent vapors
- Do not return unused material to container

Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

## 4. TECHNICAL DATA

### Applicable Standard

ASTM C 309, Type 1

ASTM C 1315, Type 1, Class A

### Physical and Working Properties

Property	Observed
Solids	25%
Alkali Resistance (number of hours, Method #6081, minimum)	>50%
Salt Spray 5% Resistance	>750 hours
Dry Time, set to touch	60 minutes
Surface Gloss (2 Coats)	High
Ultraviolet Resistance (2500 angstrom lamp), 1000 hrs.	0 (Excellent)
VOC	645 g/L

Specifications are subject to change without notification. Technical data shown in product data sheets are typical but reflect laboratory test procedures conducted in laboratory conditions. Actual field performance and test results will depend on installation methods and site conditions. Field test results will vary due to critical job site factors. All recommendations, statements and technical data contained in this data sheet are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty or guaranty of any kind. Satisfactory results depend upon many factors beyond the control of LATICRETE International, Inc. User shall rely on their own information and tests to determine suitability of the product for the intended use and user assumes all risk, loss, damage, expense and liability resulting from their direct use, indirect use or consequential to their use of the product. LATICRETE shall not be liable to the buyer or any third party for any injury, loss or damage directly or indirectly resulting from use or inability to use the product.

## 5. INSTALLATION

### Freshly placed concrete

Surface must be finished to specified requirements prior to the application of LUMISEAL PLUS™. Dampen the concrete and broom out all standing water immediately prior to application. Apply one uniform coat with low pressure spray and roller after surface water glaze has disappeared. Do not dilute or puddle. Allow 4 to 6 hours between coats. Apply to freshly poured concrete after surface water has evaporated. Too much surface water can be detrimental to proper film formation.

## Existing Concrete

Surface must be degreased and cleaned of all contaminants with CITREX™ prior to the application of LUMISEAL PLUS. After dry, apply one or two uniform coats, without puddling, as needed. Allow 6-8 hours between coats. Dry to the touch in 1 hour. Sealed concrete can ready for foot traffic in 12 hours. May require multiple coats.

## Cleaning

Clean applicator equipment with xylene\* or other solvent before sealer dries.

\*Caution: Xylene is toxic and flammable

## 6. AVAILABILITY AND COST

### Availability

L&M™ and LATICRETE® materials are available worldwide.

### For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at

[www.lmcc.com](http://www.lmcc.com)

### Cost

Contact a LATICRETE Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM:

DS 230.13: LATICRETE Product Warranty

## 8. MAINTENANCE

Non-finish LATICRETE and LATAPOXY® installation materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

Periodic light applications are recommended to maintain gloss and protection.

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 235

Telephone: +1.203.393.0010, ext. 235

Fax: +1.203.393.1948

### Technical and Safety Literature

To acquire technical and safety literature, please visit our website at [www.laticrete.com](http://www.laticrete.com).

## 10. FILING SYSTEM

Additional product information is available on our website at [www.laticrete.com](http://www.laticrete.com). The following is a list of related documents:

DS 230.13: LATICRETE Product Warranty

DS 176.6: CITREX